

Comparison of new and recycled (blue) polyethylene terephthalate (PET) (100 mg)

Sample: 220°C, Valve: 260 °C, Purge: 20 min at 20 ml/min, Desorb: 7 min at 260 °C,

Splitflow: 20 ml/min, Trap: Tenax TA,1K

Column: DB 1, 60 m, 0,32 mm, 0,25 µm, 120 kpa He,

Temp. program: 40°C/6min > 10 °/min > 320°C/15min

Detector: FID

